

PARADIENE 20 HT TG



Commercial Product Data Sheet

Product Description

Paradiene 20 HT TG is a high performance torch grade modified bitumen base ply designed for use in homogeneous multi-layer modified bitumen roof membrane systems. Paradiene 20 HT TG consists of a fiberglass scrim/fiberglass mat composite impregnated and coated with high quality styrene-butadiene-styrene (SBS) modified bitumen. The top surface is covered with a silica parting agent. The back surface is coated with a high performance modified asphalt adhesive layer specially formulated for torch applications. The adhesive layer is manufactured using a special process that embosses the surface with a grooved pattern to provide optimum burnoff of the plastic film and maximize application rates.

Paradiene 20 HT TG is available with Siplast RoofTag RFID roof asset technology on a Special-Made-To-Order basis. See RoofTag Commercial Product Data Sheet for more information.

Product Uses

Paradiene 20 HT TG is the first ply of Siplast Paradiene 20 HT TG/30 TG Systems, and is lapped 3 inches (7.6 cm) side and end. Paradiene 20 HT TG is specifically designed for high tensile requirements and for use in conjunction with torchable Siplast Paradiene Roof Systems requiring extended warranties. Paradiene 20 HT TG is torch applied to approved substrates. Contact Siplast for specific approval on product uses.

Product Approvals

Contact Siplast for specific information regarding FM Class 1 windstorm resistance classifications.

Paradiene 20 HT TG is classified by Underwriters Laboratories for use in cUL_{us} Classified Siplast Paradiene 20 HT TG/30 TG and Paradiene 20 HT TG/30 FR TG Roof Systems. Siplast Paradiene 20 HT TG/30 FR TG Roof Systems have been classified by Underwriters Laboratories as Class A roofing systems over non-combustible, insulated non-combustible, and insulated combustible decks, and as Class B roofing systems over combustible decks. Siplast Paradiene 20 HT TG/30 TG Roof Systems have been classified as Class C roofing systems over combustible, non-combustible, and insulated combustible decks.

Paradiene 20 HT TG meets or exceeds the requirements of ASTM D6163 Type II, Grade S, and CSA A123.23-15 Type A, Grade 2 for SBS-modified bituminous sheet materials using glass fiber reinforcements.

Siplast Roof Systems have also received the approval of many regional and local code authorities. Contact Siplast for more information.

COMMERCIAL PRODUCT INFORMATION

| | | | |
|-----------------------------|----------------------|--------------------------|--|
| Unit: | Roll | | |
| Coverage: | 1.0 Square | (9.3 m ²) | |
| Coverage Weight Per Square: | Min: 76 lb | (3.7 kg/m ²) | |
| Roll Length: | Min: 33.5 ft | (10.21 m) | |
| Roll Width: | Avg: 3.28 ft | (1.00 m) | |
| Thickness: | Avg: 114 mils | (2.9 mm) | |
| | Min: 110 mils | (2.8 mm) | |
| Selvage Width: | N/A | | |
| Selvage Surfacing: | N/A | | |
| Top Surfacing: | Silica Parting Agent | | |
| Back Surfacing: | Polyolefin Film | | |

Lines: Two laying lines are placed 3 in (7.6 cm) and 4 in (10.2 cm) from each edge of the material. The line color for this material is green.

Packaging: Rolls are wound onto a compressed paper tube. The rolls are placed upright on pallets cushioned with corrugated cardboard and are adhered with adhesive at the labels. The top of the palletted rolls is covered with Kraft paper. The palletted material is protected by a heat shrink polyethylene shroud.

Pallet: 41 in X 48 in (104 cm X 122 cm) wooden pallet
Number Rolls Per Pallet: 25
Number Pallets Per Truckload: 18
Minimum Roll Weight: 76 lb (34.5 kg)

Storage and Handling: All Siplast roll roofing products should be stored on end on a clean flat surface. Care should be taken that rolls are not dropped on ends or edges and are not stored in a leaning position. Deformation resulting from these actions will make proper installation difficult. All roofing should be stored in a dry place, out of direct exposure to the elements, and should not be double stacked. Material should be handled in such a manner as to ensure that it remains dry prior to and during installation.

Current copies of all Siplast Commercial Product Data Sheets are posted on the Siplast Web site at www.Siplast.com.

Rev 6/2019

PARADIENE 20 HT TG

Physical and Mechanical Properties

| UNITED STATES TEST STANDARDS | | | CANADA TEST STANDARDS | |
|--|---|--------------------------|--|---|
| Property (as Manufactured) | Values/Units | Test Method | Property (as manufactured) | Test Method CSA A123.23-15 Values/Units |
| Thickness (minimum) | 110 mils (2.8 mm) | ASTM D5147 section 6 | Thickness (minimum) | 2.8 mm (110 mils) |
| Thickness (average) | 114 mils (2.9 mm) | ASTM D5147 section 6 | Thickness (average) | 2.9 mm (114 mils) |
| ¹ Peak Load @ 73.4°F (23°C) (average) | 80 lbf/inch (14.1 kN/m) | ASTM D5147 section 7 | ¹ Peak Load 23°C (73.4°F) (average) | 14.1 kN/m (80 lbf/inch) |
| ¹ Peak Load @ 0°F (-18°C) (average) | 150 lbf/inch (26.5 kN/m) | ASTM D5147 section 7 | ¹ Peak Load @ -18°C (0°F) (average) | 26.5 kN/m (150 lbf/inch) |
| ¹ Elongation @ Peak Load, 73.4°F (23°C) (average) | 5% | ASTM D5147 section 7 | ¹ Elongation @ Peak Load, 23°C (73.4°F) (average) | 5% |
| ¹ Elongation @ Peak Load, 0°F (-18°C) (average) | 4% | ASTM D5147 section 7 | ¹ Elongation @ Peak Load, -18°C (0°F) (average) | 4% |
| ¹ Ultimate Elongation @ 73.4°F (23°C) (average) | 50% | ASTM D5147 section 7 | ¹ Ultimate Elongation @ 23°C (73.4°F) (average) | 55% |
| ¹ Tear Strength (average) | 120 lbf (0.54 kN) | ASTM D5147 section 8 | N/A | N/A |
| Water Absorption (maximum) | 1% | ASTM D5147 section 10 | N/A | N/A |
| Dimensional Stability (maximum) | 0.1% | ASTM D5147 section 11 | Dimensional Stability (maximum) | 0.1% |
| Low Temperature Flexibility (maximum) | -15°F (-26°C) | ASTM D5147 section 12 | Low Temperature Flexibility (maximum) | -26°C (-15°F) |
| Compound Stability (minimum) | 250°F (121°C) | ASTM D5147 section 16 | Compound Stability (minimum) | 121°C (250°F) |
| Coating Thickness - Back Surface | ≥ 40 mils (1 mm) | ASTM D5147 section 17 | Coating Thickness - Back Surface | 1 mm (≥ 40 mils) |
| Cyclic Fatigue | Paradiene 20 bonded to Paradiene 30 FR with an approved method of attachment, passes ASTM D5849 both as-manufactured and after heat conditioning according to ASTM D5147. | | | |

1. The value reported is the lower of either MD or XD.



The above properties have been validated by PRI and are under continuous follow-up to ensure compliance. The product has been validated to meet ASTM D6163-08, TYPE II, GRADE S.